

# CLASS A SUPERSTRENGTH GROUT

## Construction Grade Non-Shrink Grout

**Description:**

**EPIREZ® Class A Superstrength Grout** is a higher strength premixed cement based, non-ferrous, non-shrink grout, exhibiting good flow characteristics. This extra performance grout offers the advantage of low water requirements and high compressive strengths.

**Class A Superstrength Grout** should be specified for construction site applications demanding higher performance.

**Class A Superstrength Grout** is supplied ready-to-use as a dry powdered product requiring only the addition of water to be used for a wide range of applications.

**Intended Use:**

- Column base plates
- Anchoring fixings
- Bolt holes
- Tilt up panels and other joints
- Underpinning
- Concrete repair

**Product Features:**

- **High strength increase of up to 34% from Class A General Purpose Grout**
- **Non-shrink**
- **Good flow, good base plate contact**
- **High early strength 50MPa in one day (Dry pack)**
- **Super strength 91 MPa in 28 days (Dry pack)**
- **Low water / cement ratio – high density / super strength**
- **Chloride free no re-bar corrosion**
- **Non-ferrous – non staining**
- **Versatile dry pack / trowel / pour**

**Typical Physical Properties:**

**General Properties**

Work Time	20 minutes at 25°C
Initial Set	1 hour at 25°C (Flowable)
Final Set	3 hours at 25°C (Flowable)

**Water Ratio**

Dry Pack	2.0Ltr / 20kg
Trowellable	3.0Ltr / 20kg
Flowable	4.0Ltr / 20kg

**Typical Performance**

Compressive Strength (AS 1478.2 – 2005)	2.0 Ltr Water / 20kg	3.0Ltr Water / 20kg	4.0Ltr Water / 20kg
<b>1 day</b>	<b>50 MPa</b>	<b>34 MPa</b>	<b>17 MPa</b>
<b>7 days</b>	<b>82 MPa</b>	<b>62 MPa</b>	<b>36 MPa</b>
<b>28 days</b>	<b>91 MPa</b>	<b>70 MPa</b>	<b>45 MPa</b>

**AUSTRALIA**  
 ITW Polymers & Fluids  
 100 Hassall Street  
 Wetherill Park NSW 2164  
 Phone (02) 9757 8800  
 www.itwpcf.com.au

**NEW ZEALAND**  
 ITW Polymers & Fluids  
 Unit 2 / 38 Trugood Drive  
 East Tamaki 2013, Auckland  
 Phone (09) 272 1945  
 www.itwpcf.co.nz

**Estimating Data**

Consistency	Water / 20kg bag	Litres of grout / bag	No. of bags / m <sup>3</sup>
Dry Pack	1.8 – 2.2 litres	10.2	98
Trowellable	2.8 – 3.2 litres	10.6	94
Flowable / Pourable	4 litres	11.6	86

**Surface Preparation:**
**Foundation Preparation**

All surfaces should be free from oil, grease or loose material. If the concrete surface is loose, defective or has laitance, it should be cleaned to a sound base. Bolt holes or fixing pockets should be blown clean of any dirt or debris.

Several hours prior to grouting, the prepared foundation should be flooded for pre-soaking with fresh water. Immediately prior to grouting, any standing water should be removed. Inspect pockets and bolt holes for water removal.

Surface preparation guidelines cannot cover all site or field contingencies and it is always recommended that an on-the-spot adhesion test be performed as part of the Standard Quality Assurance audit for the project.

**Mixing Instructions:**
**Temperature must be above 5°C for the mixing and placement of grout.**

**EPIREZ® Class A Superstrength Grout** should be thoroughly mixed to the desired consistency by varying the amount of water used. Do not exceed recommendations.

Grout should be mixed using either a grout mixer or a suitable power mixer. Do not mix more than 5 minutes (do not remix). Once mixing and placing the grout has begun, it should be a continuous operation. Do not mix more grout than can be placed within 20 minutes.

Ensure that machine capacity and manpower is adequate to enable grouting to be carried out as a continuous operation.

Observe the accurate gauging of water addition and the mixing time. When using a mechanical mixer to prepare the grout, add approximately 90% of the recommended water requirement to the mixer first and then add the dry powder. Mix for 2 minutes before adjusting the consistency with the remainder of the water.

Mix until homogeneous for at least another 3 minutes.

**Application Instructions:**
**Placement**

To ensure continuous grout flow any bolt holes should be pre-grouted level with the substrate. Sufficient grout must be available prior to commencement and the time taken to pour a mix balanced with the time taken to prepare the next one.

Pour from one side only to eliminate the creation of voids by entrapment of air or any surplus pre-soaking water.

A grout head must be maintained at all times so that a continuous grout front is achieved.

Make certain that the mixed grout is placed promptly (within 30 minutes of mixing) and continuously before expansion commences.

Grout bed should be finished level with the underside of the baseplate.

**AUSTRALIA**

ITW Polymers & Fluids  
100 Hassall Street  
Wetherill Park NSW 2164  
Phone (02) 9757 8800  
www.itwpf.com.au

**NEW ZEALAND**

ITW Polymers & Fluids  
Unit 2 / 38 Trugood Drive  
East Tamaki 2013, Auckland  
Phone (09) 272 1945  
www.itwpf.co.nz

**Curing**

After grout has been placed, cover all exposed grout with wet burlap and plastic to prevent moisture loss. Maintain until grout has hardened. After cutting back or finishing, continue curing, for a minimum of 24 hours with wet burlap followed by application of a concrete curing compound to ensure long term curing. Failure to prevent early moisture loss can result in plastic cracking, drying shrinkage, cracks in grout shoulders and a possible reduction in ultimate strength development. In-service operation may commence once required grout strength has been reached.

The figures quoted for work time, flow, set time, yield and strength development are not definitive. They are dependent on job site conditions and will vary accordingly. In all cases we endeavour to provide typical figures for use as a guide.

**Clean Up:**

Grout should be removed from tools and equipment immediately after use with clean water.

**Storage:**

Store in dry conditions between 10°C and 30°C. Protect from frost. When stored in original sealed containers, the minimum shelf life is 12 months.

**Warranty:**

Epirez will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

**Disclaimer:**

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Polymers & Fluids and EPIREZ® makes no representations or warranties of any kind concerning this data.

**Order****Information:**

20kg bag                      E991627

**Health &  
Safety****Information:**

For Health & Safety information, refer to Safety Data Sheet available from ITW Polymers & Fluids upon request or available on our website [www.epirez.com.au](http://www.epirez.com.au) or [www.epirez.co.nz](http://www.epirez.co.nz)

**AUSTRALIA**

ITW Polymers & Fluids  
100 Hassall Street  
Wetherill Park NSW 2164  
Phone (02) 9757 8800  
[www.itwpf.com.au](http://www.itwpf.com.au)

**NEW ZEALAND**

ITW Polymers & Fluids  
Unit 2 / 38 Trugood Drive  
East Tamaki 2013, Auckland  
Phone (09) 272 1945  
[www.itwpf.co.nz](http://www.itwpf.co.nz)